

HPM[®] 270 NICKEL



HPM[®] 270 NICKEL (UNS N02270)

HPM[®] 270 Nickel is the highest purity Nickel. The controlled low impurity level provides uniform and repeatable mechanical, electrical, and magnetic properties. The material has excellent corrosion resistance with high thermal and electrical conductivities. A high thermal coefficient of electrical resistance makes it suitable for temperature sensors, and electronic components.

GENERAL INFORMATION

The alloy can be formed by all conventional cold forming methods, and can be joined by resistance welding, brazing and soldering. The corrosion resistance is generally very good in most mediums, although, it is subject to intergranular embrittlement by sulfur compounds above 315°C.

AVAILABILITY

HPM[®] 270 Nickel is available from Hamilton Precision Metals as strip product in thicknesses from 0.0005" to 0.020" (0.0127 mm to 0.508 mm) in widths up to 12.0" (304.8 mm). It is available as foil as thin as 0.000100" (0.00254 mm) in 4.0" (101.6 mm) maximum width. The material conforms to ASTM F3, and UNS N02270.



Technical Data

TYPICAL MECHANICAL PROPERTIES ¹		
	ANNEALED	COLD ROLLED
Ultimate Tensile Strength	55,000 PSI	105,000 PSI
Yield Strength (0.2% Offset)	15,000 PSI	100,000 PSI
Elongation in 2" *	40%	2%
Modulus of Elasticity (Tension)	30.1 X 10 ⁶ PSI	-
Poisson's Ratio	0.31	-

*The measured elongation will be less as thickness decreases to 0.002" and less.

¹ These values may be adjusted by control of process variables – consult HPM for desired values.

NOMINAL COMPOSITION	
Nickel	99.9%
Manganese	0.01%
Iron	0.01%
Carbon	0.01%

PHYSICAL PROPERTIES ²	
Density	0.322 lbs./cu.in.
Melting Point (Approx.)	1450°C
Electrical Resistivity @ R.T.	7.4 Microhm · cm
Temperature Coefficient of Resistivity (TCR) (0°C to 25°C)	6000 ppm/°C
Thermal Expansion Coefficient (20°C to 100°C)	14.0 X 10 ⁻⁶ /°C
Thermal Conductivity @ R.T.	86.3 W/m · K
Curie Temperature	355°C
DC Magnetic Properties Coercivity	3.0 oersteds
DC Magnetic Properties Saturation Induction	6050 Gauss
Magnetic Attraction	Yes
Specific Heat	0.110 gram · cal./°C

² Typical values to guide alloy selection but are not a guarantee of minimum or maximum.

Disclaimer: The information contained within this data sheet is for guidance only and is not intended for warranty of individual application - express or implied. HPM[®] Ni 270 is a registered trademark of Hamilton Precision Metals | AMETEK Specialty Metal Products.