

HPM® 233 NICKEL



HPM® 233 NICKEL (UNS N02233)

HPM 233® Nickel is a commercially pure wrought Nickel with low carbon. The material has excellent corrosion resistance with high thermal and electrical conductivities. A high thermal coefficient of electrical resistance makes it suitable for temperature sensors, and electronic components.

GENERAL INFORMATION

The alloy can be formed by all conventional cold-forming methods and can be joined by welding, brazing and soldering. The corrosion resistance is generally very good in most mediums, although it is subject to intergranular embrittlement by sulfur compounds above 315 °C.

AVAILABILITY

HPM 233® Nickel is available from Hamilton Precision Metals as strip product in thicknesses from 0.0005" to 0.020" (0.0127 mm to 0.508 mm) in widths up to 12.0" (304.8 mm). It is available as foil as thin as 0.000100" (0.00254 mm) in 4.0" (101.6 mm) maximum width.

The material conforms to ASTM B162, ASTM F3, and UNS N02233.



Technical Data

TYPICAL MECHANICAL PROPERTIES ¹		
	ANNEALED	COLD ROLLED
Ultimate Tensile Strength	55,000 PSI	110,000 PSI
Yield Strength (0.2% Offset)	15,000 PSI	100,000 PSI
Elongation in 2" *	40%	2%
Modulus of Elasticity (Tension)	30 X 10 ⁶ PSI	-
Poisson's Ratio	0.28	-

*The measured elongation will be less as thickness decreases to 0.002" and less.

¹ These values may be adjusted by control of process variables – consult HPM for desired values.

NOMINAL COMPOSITION	
Nickel	99.7%
Manganese	0.1%
Iron	0.05%
Carbon	0.01%

PHYSICAL PROPERTIES ²	
Density	0.321 lbs./cu.in.
Melting Point (Approx.)	1445 °C
Electrical Resistivity @ R.T.	7.7 Microhm · cm
Temperature Coefficient of Resistivity (20° to 95 °C)	5500 PPM/°C
Thermal Expansion Coefficient (20° to 100 °C)	13.3 X 10 ⁶ /°C
Thermal Conductivity @ R.T.	80.7 W/m · K
Curie Temperature	350 °C
Magnetic Attraction	Yes

² Typical values to guide alloy selection but are not a guarantee of minimum or maximum.

Disclaimer: The information contained within this data sheet is for guidance only and is not intended for warranty of individual application - express or implied. HPM® 233 is a registered trademark of Hamilton Precision Metals | AMETEK Specialty Metal Products.